

Product Information

▶ AEROSIL® 200 Pharma Colloidal Silicon Dioxide

AEROSIL® 200 Pharma is a high purity amorphous anhydrous colloidal silicon dioxide for use in pharmaceutical products (tested according to USP/NF, Ph. Eur. Monograph 0434 and JP).

Applications and Properties

Applications

- Pharmacy, especially semi-solid and liquid dosage forms

Properties

- Used as viscosity increasing agent to thicken and thixotropize liquids
- Improves storage and temperature stability of semi-solid and liquid dosage forms
- Improves distribution of active pharmaceutical ingredients
- Dessicant for moisture-sensitive actives.
- Free flow and anti-caking agent to improve powder properties

Physico-chemical Data

Properties	Unit	Typical Value
Specific surface area (BET)	m ² /g	200 ± 25
Tamped density* acc. to DIN EN ISO 787/11, Aug. 1983	g/l	approx. 50
pH Tested according to Ph. Eur., USP/NF		3.5 - 5.5
Chloride Tested according to Ph. Eur.; JP	ppm	≤ 250; ≤ 110
Heavy Metals Tested according to Ph. Eur.; JP	ppm	≤ 25; ≤ 40
SiO₂ - content Tested acc. to Ph. Eur., USP/NF; JP	wt. %	99.0 - 100.5; ≥ 98.0
Loss on Drying (moisture)* Tested according to USP/NF; JP	wt. %	≤ 2.5; ≤ 7.0
Loss on Ignition Tested acc. to Ph. Eur.; USP/NF; JP	wt. %	≤ 5.0; ≤ 2.0; ≤ 12.0
As - content Tested according to USP/NF; JP	ppm	≤ 8.0; ≤ 5.0
Residual Solvents Tested according to USP/NF		pass
Volume Test Tested according to JP	ml	≥ 70
Ca - content Tested according to JP		pass
Fe - content Tested according to JP	ppm	≤ 500
Al - content Tested according to JP		pass

* ex plant

The data represents typical values (no product specification)

Safety and Handling

With every sample or initial shipment of our products we will send a Material Safety Data Sheet. Of course, you can also request an MSDS or any other information regarding product safety at any time, or download it as a registered user at www.aerosil.com.

Packaging and Storage

AEROSIL® 200 Pharma is supplied in multiple layer 10 kg bags. We recommend to store the product in closed containers under dry conditions and to protect the material from volatile substances. AEROSIL® 200 Pharma should be used within 2 years after production.

Registration

AEROSIL® 200 Pharma					
CAS-No.	EINECS	TSCA (USA), AICS (Australia), DSL (Canada)	ENCS (Japan)	ECL (Korea)	IECS (China)
112 945-52-5 7631-86-9	231-545-4	Registered	1-548	KE-30953 (KE-31032)	Registered

► For further information please contact:

Customer Service

*Europe, Central- and
Southamerica, Africa*

Evonik Degussa GmbH
Inorganic Materials
Weissfrauenstrasse 9
D-60287 Frankfurt am Main,
Germany
Phone: +49 69/218-25 32
Fax: +49 69/218-6 25 32
E-Mail: aerosil@evonik.com
<http://www.aerosil.com>

NAFTA

Evonik Degussa Corporation
Inorganic Materials
379 Interpace Parkway,
P. O. Box 677
Parsippany, NJ 07054-0677
Phone: +1 (800) AEROSIL
Phone: +1 (973) 541-8510
Fax: +1 (973) 541-8501

Asia

NIPPON AEROSIL CO., LTD.
Sales & Marketing Division
P. O. Box 7015
Shinjuku Monolith 13F
3-1, Nishi-Shinjuku 2-chome
Shinjuku-ku, Tokyo
163-0913 Japan
Phone: +81-3-3342-1763
Fax: +81-3-3342-1772

Technical Service

*Europe, Central- and
Southamerica, Africa*

Evonik Degussa GmbH
Inorganic Materials
Rodenbacher Chaussee 4
P. O. Box 1345
D-63403 Hanau-Wolfgang,
Germany
Phone: +49 61 81/59-39 36
Fax: +49 6181/59-40 96

NAFTA

Evonik Degussa Corporation
Inorganic Materials
2 Turner Place
Piscataway, NJ 08855-0365
Phone: +1 (888) SILICAS
Phone: +1 (732) 981-5000
Fax: +1 (732) 981-5275

Asia (without Japan)

Evonik Degussa China Co. Ltd.
Chundong Road,
Xinzhuang Industry Park 55
201108 Shanghai
China
Phone: +86 21/6119 1065
Fax: +86 21/6119 1075

Japan

NIPPON AEROSIL CO., LTD.
Applied Technology Service
3 Mita-cho
Yokkaichi, Mie
510-0841 Japan
Phone: +81-593-45-5270
Fax: +81-593-46-4657

Please visit our website www.aerosil.com to find your local contact.

This information and all further technical advice are based on Degussa's present knowledge and experience. However, Degussa assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, Degussa disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. DEGUSSA SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. Degussa reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.